

MICODUR

			Mineral Micodur
	Dimensions & thickness	EN 16511	905 × 445 × 7,2 mm
	Classification	EN 16511	Domestic 23 / Commercial 33
	Total weight	EN 430	ca. 12 000 g/m ²
	Abrasion resistance	EN 14354 & EN 13329	> 10 000 WR4 AC5
	Impact sound reduction	EN ISO 717-2	ca. 19 dB
	Effect of castor chair	EN 425	fulfil
	Reaction of fire	EN ISO 9239-1	A2fl-s1
	Thermal resistance	EN 12524	ca. 0,05 m ² K/W
	Dimensional stability	EN 434	< 0,03 %
	Residual indentation	EN 433	0,00 mm
	Lightfast	ISO 105	7 / 8
	Resistance to chemicals	EN 423	very good resistance
	Emissions value		< 100 ppm laut AgBB
	Swellness value 24h	EN 317	0 %
	Locking strength	ISO 24334	> 500 kg/lfm – kg/m
	Reaction to static electricity	EN 1815	< 2,0 kV antistatic
	Micro scratch resistance	EN 16094	MSR-A1/MSR-B1
	Effect of a furniture leg	EN 424	no damage shall be visible
	Slip resistance	EN 13501 -1	Klasse DS
	Effect of stains	EN 438-2:2016	Grad 5 / 5